

COLOUR CHART

PVC Trade Tile Trim



MADE IN THE UK



✓ Better Quality ✓ Better Value ✓ British Made

• T: 01543 500893 • F: 01543 500894 • E: sales@tilerite.co.uk • W: tilerite.co.uk



WHITE

- 6mm - ETE803
- 7mm - ETE001
- 9mm - ETE003
- 12mm - ETE010



SOFT PEACH

- 7mm - ETE002
- 9mm - ETE004
- 12mm - ETE011



IVORY

- 7mm - ETE005
- 9mm - ETE006
- 12mm - ETE012



AMERICAN BONE

- 7mm - ETE017
- 9mm - ETE014
- 12mm - ETE015



BLACK

- 7mm - ETE018
- 9mm - ETE013
- 12mm - ETE016

TECHNICAL DETAILS: PVC is particularly suitable for a wide range of applications due to its excellent chemical resistance.

Exceptions: Not recommended for use above 60°C. Resistant to most oils, alcohols, petrol and fats. It is unsuitable for use in contact with aromatic and chlorinated hydrocarbons, ketones, nitrocompounds, esters and cyclic ethers.

GRADE: LG0000 - The raw material used in the manufacture of these products is calcium zinc stabilized formulation and contains no lead or substances of very high concern (SVHC). It is fully compliant with WEEE & RoHS Directives.

DESCRIPTION: Calcium Zinc stabilized Extrusion grade PVC, suitable for indoor use.

MAINTENANCE: Tile Trade Trim requires no special maintenance. Cleaned periodically using a PH neutral detergent to maintain the appearance. Regular cleaning aids the longevity of the profile and ensures there is no corrosion that could affect safety.

PROPERTY	UNIT	RESULT	TEST METHOD
Specific Gravity (According to Colour)	G/ccM	1.42	ASTM D692
Vicat Softening Point	°C	78	BS2782:120B
Apparent Modulus of Elasticity	Mpa	2300	BS2782:335A
Tensile Strength	Mpa	40	BS2782:320C
Impact Strength	KJ/M2	12	BS2782:359
Heat Stability	Mins	88	BS2782-130A