

SPECIFICATION SHEET

FLEXIBLE BATH SEAL (FBS718 / FBS689)



• T: 01543 500893 • F: 01543 500894 • E: sales@tilerite.co.uk • W: tilerite.co.uk

ITEM		CONDITION	SPECIFICATION	STANDARD
BASIC COMPOSITION			MONO ELEMENT BUTYL-LATEX	
HEAT RESISTANCE		90+/-2°C	NO FLOWING AND NO CRACKLING	ASTM C792-93
LOW TEMPERATURE FLEXIBILITY		-40°C, 72H	NO-CRACKLE ON SURFACE	ASTM C734-01
APPLICATION TEMPERATURE			-40° TO 90°C	
ELONGATION		23°C 250mm/min	600	ASTM C736-00
CLARITY HUMIDITY		23°C 300mm/min	15	GB/T 12952-91
TENSILE STRENGTH		23°C 50mm/min	110	ASTM C719-93
PEELING FORCE		23°C 300MM/MIN	15	ASTM D3330-02
N/C SHEARING FORCE	STEEL SLAB	23°C 250mm/min	53.8	GB/T 12952-91
	GLASS		47.2	
	CEMENT SLAB		45.9	
	ADUMBRAL LPLATE		48.2	
	STAINLESS PLATE		51.7	
CORROSION	ZIN-PLATE AL-CASE	IMMERSE IN DISTILED WATER 168H	NO SCAR NO CORROSION	
	CUCASE	70+/-2°C, 168h	NO CHANGE IN BLACK NO ETCHING	

Store in a dry and ventilated place at room temperature. Avoid sunlight exposure. Storage life is 2-3 years.